

Plastifloor® - 112 (GB)

Fast-curing 2-component- adhesive primer
for concrete and cement screed

PLASTI CHEMIE
Produktionsgesellschaft mbH

Application: Primer 112 serves as adhesive primer for Plastifloor® coatings, especially on cement-bound substrates.

Properties: Primer 112 is a reactive methacrylate resin that also cures fast on low temperatures.

Characteristics:

Form of delivery	slightly cloudy liquid
Flow time	30-40 sec. (20°C), DIN cup 4mm
Curing	10 – 20 min at 20°C and 2% hardener
Shelf life	dark at < 20 °C 6 months maximum
Bundle	180kg drums 25 kg, 10 kg pails

Initiator/Hardener: Hardening powder 50W (BPO), depending on temperature

Suggested formulation

PF 112

primer:

Primer 112 can be processed with hardener 50 W. Hardener quantity must be adjusted to the respective object temperature (see table). At temperatures below + 5°C, accelerator B101 can additionally be added must be added (~ 0.5 % at 0 °C up to 3 % at –30 °C) with retention of 6 PBV hardener powder.

After mixing in the hardener powder, Plastifloor® 112 is being equally and thinly dispersed with a roller or rubber squeegee (300-600 g/m²). Consumption must be adjusted individually. On extremely absorbent substrates, prime twice in order to achieve a thin but closed film that bonds the broadcasting material. We recommend slightly broadcasting the primer with quartz sand (size 0.7-1.2 mm). If only thin sealers are to be applied, we recommend using quartz sand in size 0.4 – 0.8 mm. This work step ensures an absolutely solid bond between primer and the following coating.

Consumption ~ 300-600 g/m² per work step

Plastifloor® - 112 (GB)

Fast-curing 2-component- adhesive primer
for concrete and cement screed

PLASTI CHEMIE
Produktionsgesellschaft mbH

Suggested formulation:

8l primer 112
240 ml hardener 50W (at 20°C ground temperature)

Pot life and curing times depending on temperature:

Further coating layers with Plastifloor must only be applied after the previous layers have completely cured.

Temperatur [°C]	Hardener [Vol%]*	Pot life [min]	Curing time [min]
+0	6	ca. 11	ca. 30
+5	5	ca. 8	ca. 30
+10	4	ca. 8	ca. 30
+15	3	ca. 7	ca. 25
+20	3	ca. 6	ca. 20
+25	2	ca. 6	ca. 20

*) Hardener quantity calculated according to Plastifloor® 112

**) temperature refers to resin, surface and air temperature

Attention:

Hardener quantities below 2 Vol. % may cause polymerization failures!

Storage:

The handling-regulations for highly flammable materials apply to methacrylate – resins. Plastifloor resins are to be stored cool, protected against direct sunlight and preferably at temperatures of 15-20 °C. During storage paraffin - particles and filler - materials may precipitate. Thus before processing, containers have to be stirred up well. Please mind the advice on our safety data sheets.

Plastifloor® - 112 (GB)

Fast-curing 2-component- adhesive primer
for concrete and cement screed

PLASTI CHEMIE
Produktionsgesellschaft mbH

Industrial safety:

Ensure sufficient ventilation during work. On processing, pay attention to the directives in the hazardous substances ordinance and to the indications of the Federal States Committee for industrial safety and safety engineering (LASI) as well as to our safety data sheets.

VbF: A I
GISCODE: RMA 10
Taxnumber: 3208 2010

data concerning our products and devices as well as concerning our data and procedures are based on an extensive research work and an application technology experience. We obtain these results, with which we do not take over adhesion going beyond the respective single contract, in word and writing after best knowledge, reserve ourselves we however technical changes in the course of the product development. Beyond that our application technology service stands when desired for large consultation as well as for co-operation with the solution manufacturing and application technology problems for order. That does not relieve the user however to examine our data and recommendations before their use responsible for the own use. That applies - particularly for deliveries to foreign markets - also regarding the keeping of patent rights third as well as for applications and procedures, which are not expressly in writing indicated by us. The case of loss our adhesion is limited to indemnifications of same extent, as they plan our general terms of delivery and sales with lack of Quality.

01.06.2022

3 / 3