

Plastifloor® 528 (GB)

Medium viscous PU-MMA resin for sealcoats of Plastifloor®
Coatings based on Plastifloor® 332
Particularly suitable for outside applications

Properties: Flexible topcoat, with high impact resistance, especially on Plastifloor® 332 outdoor broadcast coatings. The coating remains impact resistant over a wide temperature range. Plastifloor® 528 is also suitable as a sealant in cold storage rooms.

Characteristics of the resin as delivered:

Property	Measuring Method	Approx. value
Viscosity at 23 °C	DIN 53 015	100-140 mPa · s
Flow time at 20°C, 4 mm cup	DIN 53 211	25-35 sec
Density D ²⁰	DIN 51 757	0.94 g/cm ³
Pot life at 20°C		ca. 15 min
Curing		25-35 min.
Form of Delivery		liquid, Violet
Shelf-life		dark at < 20°C 6 months maximum
Bundle		180 kg Drums 25 kg, 10 kg Pails

Characteristics of the resin in the hardened state:

Property	Measuring Method	Approx. value
Strain at break	EN ISO 527	~4%
Tensile strength	EN ISO 527	~22.0 MPa
E-modul	EN ISO 527	820 MPa
Water Absorption, 4 days	DIN 53 495	100 mg
Shore-D	DIN 53 505	70-85 Units

Initiator/Hardener: Hardener Powder (BPO), depending on temperature

Processing: For proper cure, a minimum of 400 g/m² of sealer must be applied per roll. To provide the necessary slip resistance and to avoid yellowing and flaking, the maximum layer thickness is limited to 800 g/m². Best results are obtained at 700 g/m² when applied with a short hair roller (polyamide gold strip) on sand broadcast coatings (0.7 - 1.2 mm grain).

Plastifloor® 528 (GB)

Medium viscous PU-MMA resin for sealcoats of Plastifloor®

Coatings based on Plastifloor® 332

Particularly suitable for outside applications

Preparation:

8 L Plastifloor® 528

800 mL Hardener 50W or 160 mL Hardener/M

Pot life and Hardening time

depending on the
temperature:

Temperatur [°C]	Hardener [Vol%]	Hardener [wt%]	Pot life [min]	Curing time [min]
+5	2.0	1.3	ca. 30	ca. 50
+10	1.5	1.0	ca. 20	ca. 40
+20	1.0	0.7	ca. 15	ca. 30
+25	1.0	0.7	ca. 12	ca. 20

- Hardener quantity calculated according to Plastifloor® 528
- Temperature refers to resin, surface and air temperature

Notes:

To avoid yellowing, the specified hardener quantities must be strictly adhered to. Good ventilation during application will ensure good curing. Due to the thermoplastic nature of MMA resins, black streaks (skid marks!) may appear under the pressure of forklift traffic.

Storage:

Methacrylate resins are subject to the regulations for handling of highly flammable materials. Plastifloor® resins must be stored cool, if possible, at temperatures between 15 – 20° C. Keep away from direct sunlight. Paraffin particles may be deposited during storage. Stir the material well before use. Please follow the instructions in our Safety Data Sheet.

Plastifloor® 528 (GB)

Medium viscous PU-MMA resin for sealcoats of Plastifloor®

Coatings based on Plastifloor® 332

Particularly suitable for outside applications

Industrial safety:

Provide adequate ventilation during work. During processing, observe the regulations of the Hazardous Substances Ordinance, the instructions of the Federal State Committee for Occupational Safety and Safety Technology (LASI), and our safety data sheets.

VbF: A I

GISCODE: RMA 10

HS-code: 3208 2010

CE	
Plasti Chemie International GmbH • Falgardring 1 • 08223 Falkenstein • Germany	
EN 13813, SR-B2, 0-AR0, 5-IR12	
Plastifloor® 528	
Synthetic resins for internal uses (Application in accordance with the newest technical information)	
Reaction to fire:	E ₁
Wear resistance (Abrasion Resistance):	AR 0.5
Impact resistance:	IR 12
Tensile bond strength:	B 2.0

CE-labelling

data concerning our products and devices as well as concerning our data and procedures are based on an extensive research work and an application technology experience. We obtain these results, with which we do not take over adhesion going beyond the respective single contract, in word and writing after best knowledge, reserve ourselves we however technical changes in the course of the product development. Beyond that our application technology service stands when desired for large consultation as well as for co-operation with the solution manufacturing and application technology problems for order. That does not relieve the user however to examine our data and recommendations before their use responsible for the own use. That applies - particularly for deliveries to foreign markets - also regarding the keeping of patent rights third as well as for applications and procedures, which are not expressly in writing indicated by us. The case of loss our adhesion is limited to indemnifications of same extent, as they plan our general terms of delivery and sales with lack of quality.